

ASOCRET®-BIS-5/40

ASOCRET®-FM40/INDUCRET®-BIS-5/40

REPAIR MORTAR FOR VOIDS FROM 5-40 MM DEPTH

Product Description:

- Water impermeable
- Water vapour permeable.
- Resistant to frost and de-icing salts.
- Impairs the passage of CO₂.
- High resistance to carbonation.
- Trowel and spray applications.

Areas of Application:

ASOCRET®-BIS-5/40 is used as an anti-sag re-profiling mortar for vertical, horizontal and overhead areas for voids up to 40 mm. It is also suitable as a levelling compound on swimming pools and tanks as well as for forming pool edge details for subsequent waterproofing or tile installation.

Technical Properties:

Colour	: cement grey.
Basis	: cement.
Particle size	: up to 2 mm.
Bulk density	: 1.6 kg/dm ³ .
Wet density	: 2.1 kg/dm ³ .
Working life	: approx. 60 minutes at +20 °C
Overcoat after	: min. 1 day.
Application temp	: +5°C to +30°C.
Compressive strength*	: 24 hours approx. 19 N/mm ² 7 days approx. 35 N/mm ² 28 days approx. 42 N/mm ²

Flexural strength*	: 24 hours approx. 4 N/mm ² . 7 days approx. 8 N/mm ² . 28 days approx. 9 N/mm ² .
Tensile strength:	: 28 days approx. 1.85 N/mm ²
Overcoating with bonded waterproofing membranes/tiles	: approx. 24 hours.
Consumptions	: approx. 18 kg/m ² /mm thickness.
Cleaning	: Thoroughly clean tools with water after use.
Packaging	: 25 kg bag.
Storage	: 12 months when kept in the original unopened packaging under dry and cool conditions above +10°C.

*) at +23°C and 50 % relative humidity. Due to weather and site conditions, the given timings may be longer or shorter.

Product Preparation:

Each 25 kg ASOCRET-BIS®-5/40 requires a water quantity of approx. 3.5–3.75 l water. Initially add approx. 2.8–3.0 l water/25 kg ASOCRET-BIS®-5/40 and mix with the powder for approx. 3 minutes. Then add the remaining quantity of water and mix for a further 2 minutes to a homogenous and lump-free consistency. When mixing larger amounts, we recommend the use of a compulsory mixer. Only mix as much material as can be used within 60 minutes.

Hand Application:

ASOCRET®-BIS-5/40 is applied together with the mineral-based bonding agent ASOCRET®-BIS-0/2. ASOCRET®-BIS-0/2 is brushed into the prepared matt-damp substrate using a hard broom to give full coverage and fill surface pores. Apply the ASOCRET®-BIS-5/40 repair mortar to the required thickness whilst the bonding agent is still wet. Subsequently, compact the mortar and strike off flush with the surface. When applying to larger areas, the thickness can only be applied up to 20 mm in one layer. We recommend building up layers for thicker applications. As an alternative, applications up to 40 mm in one layer can be achieved by spraying.

Wet Spray Application Process:

When applying by wet spray techniques, the use of a mineral-based bonding agent can be skipped. Apply 2 layers of ASOCRET®-BIS-0/2 corrosion protection at least 72 hours before applying the ASOCRET®-BIS-5/40 mortar by wet spray techniques. The substrate must be matt-damp when installing ASOCRET®-BIS-5/40. Re-profiling by wet spray is carried out after the material has been mixed in a compulsory mixer with a suitable feed pump and the use of a MAWO nozzle. To ensure a regular spray pattern, the use of a high-performance site compressor is mandatory (min. 4 m³ air/ 4–5 bar operating pressure).

Without A Compulsory Mixer:

Pump system: High Comp
The Power Pump unit: XP 120
Water demand: approx. 190–200 litres/hour
Nozzle: MAWO nozzle 35/12 mm
Max hose length: 30 m
Control nozzle distance: 0.5–1.0 m

PFT Pump System:

Multi Mix compulsory mixer
Conveyor pump N2FU400/screw feed D8-1.5

Reprofiling nozzle 35/12 mm

(Reprofiling spray tool)

Max hose length: 30 m.

Control nozzle distance: 0.5-1.0 m.

Inotec Pump System:

Inomix compulsory mixer ZM80 Jet Mix

Inobeam F21 light/screw feed D8-1.5

Mortar hose 25 mm diameter

Reprofiling nozzle 35/12 mm

(Reprofiling spray tool)

Max hose length: 30 m

Control nozzle distance: 0.5–1.0 m

Material Application:

Through introduction of compressed air at the spray nozzle, the material should exit the nozzle in a uniform circular pattern. During the first spray coat application, blow holes, honeycombs, voids behind the rebar, irregularities in the wall, etc, should be filled and evened out. The second spray coat should be used to build up desired material thickness, which can then be finished with proper smoothing methods.

Post Application Treatment:

Once the ASOCRET®-BIS-5/40 has been applied, carefully protect the mortar surface from drying out too quickly by using suitable measures. This may be achieved by keeping damp for at least 3-5 days using water mist spray or wet jute sheeting or covering with other sheeting as necessary. The sheeting must fixed to the area so that there is no air exchange possible. Pay particular attention to post application treatment when the mortar surface is exposed to direct sunlight, draughts, large temperature variations and/or low humidity. If the application of a mineral based waterproof slurry is planned, then this can be applied after approx. 24 hours as an alternative post application treatment method.



Important Advice:

- Prior to commencing any concrete restoration measures, the actual condition is generally to be assessed by a specialist and/or Structural Engineer. The test record is to be made available to the applicator before starting the renovation work.
- Protect areas not to be treated from the effects of ASOCRET®-BIS-5/40.
- ASOCRET®-BIS-5/40 mortar that has already started to harden, may not be re-lifed through the addition of water or fresh mortar as there is a risk of inadequate strength development.
- Applications that are not clearly explained in this technical data sheet may only be carried out after consultation with and written confirmation from the Technical Services Department of AQUAFIN Pakistan.
- Observe pertinent regulations and guidelines.

