

# INDUFLOOR®-IB 1285

NON-TOXIC, LOW VISCOSITY, SOLVENT-FREE, MOISTURE-TOLERANT, 2-COMPONENT, PIGMENTED EPOXY RESIN-BASED PENETRATING PRIMER & SEALER, SUITABLE FOR CONTACT WITH POTABLE WATER

### Product Description:

INDUFLOOR®-IB 1285 is a low viscosity, non-toxic, 2-component, solvent-free (100% solids), odourless, low VOC, moisture-tolerant, pigmented epoxy resin-based primer and sealer. INDUFLOOR®-IB 1285 is suitable for use in potable water structures. INDUFLOOR®-IB 1285 is formulated to prime & seal concrete and masonry substrates where high performance is required. Additionally, INDUFLOOR®-IB 1285 is part of the multi-flooring system, INDUFLOOR®-IB 3359 where high adhesion to porous concrete surfaces is fundamental.

### Primary Uses:

INDUFLOOR®-IB 1285 is typically used for:

- Priming & sealing of concrete and masonry surfaces.
- Adhesion promotion between substrates and subsequent applications such as but not limited to: epoxy coatings, self-level floor toppings, floor screeds & PU floor systems.
- Bonding epoxy flooring to concrete, steel and masonry.
- Sealing concrete substrates; enhanced protection against chemical reagents, water and water-soluble salts.

### Advantages:

- Easily applied by brush or roller.
- Low VOC; odourless.
- Solvent-Free (100% solids).

- Non-toxic; suitable for contact with potable water.
- Pigmented to ensure full coverage visually.
- Rapid cure even at low temperatures, dampness or humid conditions.
- Superior adhesion to dry & damp surfaces.
- Excellent tensile & flexural strengths.
- Low viscosity; ensures effective penetration & strengthening of surface.
- Excellent anti-corrosion properties.
- Excellent resistance to water, wastewater and salt water.
- It will perform as a water-stop membrane (moisture vapour barrier).

### Standards:

INDUFLOOR®-IB 1285 is formulated to comply with all requirements of ASTM C- 881 Type I & II, Grade 1, Class B & C.

### Technical Properties:

Appearance (mixed)	: light grey liquid.
Specific gravity	: 1.40 kg/litre.
Solid content	: 100% by weight & volume.
Application temperature	: 5°C to 40°C.
Pot-life	: 60 mins at 25°C.
Full cure	: 7 days at 25°C.
Bond strength to concrete	: > 4 N/mm <sup>2</sup> .



### Application Guide:

#### Surface Preparation:

All surfaces must be sound, clean and free from dust, grease, oils, curing agents, mould release agents and other contaminations adversely affecting bond with substrate.

Steel or metal surfaces should be free from rust or scale in accordance with SA 2 $\frac{1}{2}$  (white metal finish). All adhesion preventing contaminations should be fully removed.

#### Mixing:

Stir well each of the components (separately) prior to the mixing of the two components. Empty the entire contents of component B into the canister of component A. Using an appropriate drill attached with an approved mixing paddle, mix (RPM approx. 300) the entire contents well for at least 3 to 5 minutes, until a uniform colour and consistency is achieved.

#### Placement:

Apply the properly mixed INDUFLOOR<sup>®</sup>-IB 1285 onto the prepared substrate using a suitable brush or roller. Airless spray equipment can be used in case of large areas.

Whilst the coating is still tacky, apply the subsequent floor coating, self-level floor topping, floor screed or PU flooring system. If INDUFLOOR<sup>®</sup>-IB 1285 dries out, reprime before commencement with subsequent layer.

#### Cleaning:

Clean all tools & equipment during and immediately after completion of works with INDU-UB Cleanser. Hardened material can be removed mechanically.

### Packaging:

INDUFLOOR<sup>®</sup>-IB 1285 is supplied in 6 kg packs.

### Consumption:

As a "primer": 0.25 - 0.40 kg/m<sup>3</sup>(\*).

As a "sealer": 0.25 - 0.55 kg/m<sup>3</sup> at 2 coats (\*).

[\*] Consumption depends on surface porosity, levelness, ambient & substrate temperatures.

### Storage & Shelf-life:

Both components have a shelf life of 24 months when original, unopened containers are stored in a dry, well-ventilated warehouse away from moisture, direct sunlight, and extreme temperatures (keep above 6°C & below 35°C) on pallets, elevated from the floor.

### Health & Safety:

- INDUFLOOR<sup>®</sup>-IB 1285 is non-toxic & non-hazardous during handling, storage, use and after curing.
- Do not dispense any of the components or unhardened material into water sources or onto soil. Expired or out of pot-life material should be disposed of in accordance with local environmental regulations.
- Splashes on skin can be washed with soap and clean water.
- For more details about safety requirements, please refer to a valid MSDS!